

ECO FLUID CENTER LTD.
Toll free (North America) 888 442-5008 or 416 466-3144
Fax: 416 466-3807 e-mail: info@fluidcenter.com
website: www.fluidcenter.com or www.VSGgrease.com

VSG® - THE 'GREEN' GREASE

TYPICAL TEST DATA – NLGI GRADE 1

Main ingredient: name	canola (vegetable) oil
Thickener:	calcium sulphonate
Biodegradability: % after 21 days, CEC L-33-T-82.	81
Eco-toxicity: Daphnia Magna test, 48 hours	LC50 >1,000 ppm
Rainbow Trout test, 96 hours	LC50 >93 cm ² /l
Daphnia Magna, 48 hours per EPA/600/4-90/027F	LD50 >1,000 ppm
Mysid Shrimp, 48 hours per EPA/600/4-90/027F	LD50 >1,000 ppm
Lead Content: ppm	<1 (none added)
Density: kg/L	>1.0
Color:	light tan
Odor:	similar to cooking oil
Penetration: worked at 25°C (77°F), ASTM D-217	325
Dropping Point: °C (°F), ASTM D-2265	250 (480)
Apparent Viscosity: Poise at 0°C (32°F), ASTM D-1092	
15 reciprocal seconds	429
100 reciprocal seconds	102
500 reciprocal seconds	42
Lincoln Ventmeter: psi drop @ 25°C / 0°C / -18°C (77/32/0°F)	20 / 110 / 235
USX Mobility: g/minute @ -18°C (0°F) and 21.7 kPa (150 psi)	226
Worked Stability: % change after 100,000 strokes, ASTM D-217	+2.5 (softens)
10,000 strokes with 20% water, ASTM D-217	-20 (stiffens)
Roll Stability: % change, with 50% water, ASTM D-1831	-19 (stiffens)
Water Washout: % loss at 79.4°C (175°F), ASTM D-1264	1.21
Oil Bleed: ASTM D6184, % cone oil bleed after 30 hours at 100°C (212°F)	0.87
Volatile Matter: % loss after 3 hours @ 107°C (225°F).	0.38
Timken OK Load: kg, ASTM D-2509	25
4 Ball EP: ASTM D-2596, load wear index, kgf	55
weld point, kgf	400
4 Ball Wear: ASTM D-2266, scar diameter in mm	0.42
US Navy Gear Wear: 10 lb load, mg/1000 cycles	0.57
Salt Fog: ASTM DB-117, hours to failure @ 1 mil d.f.t.	>300
Rust Protection: ASTM D-1743	pass
Copper Strip Corrosion: 24 hours at 100°C (212°F), ASTM D-4048	1b
Low Temperature Flexibility: 1 hr @ -20°F, MIL-PRF-18458C	Pass
Adhesiveness: 15 minutes at 151°F, MIL-PRF-18458	99%

Plus, no added dyes, heavy metals, chlorinated compounds, zinc compounds or sodium nitrate.

Other test data is available. If you do not see what you want, please contact us.

No warranties, express or implied, including warranties of merchantability or fitness for a particular use, are made with respect to the products described herein. Nothing contained herein shall constitute a permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.